

AZALCHID E35 - 60X

TYPE

Epoxyester based on dehydrated castor oil / soybean fatty acids (approx. 35% as triglycerides).

DELIVERY FORM

60% in xylene

FEATURES

High hardness development
Excellent chemical resistance
Quick drying
Very good adhesion

SPECIFICATION

Technical characteristics

Property	Unit	Value	Method
Appearance	-	clear viscous liquid	visual
Solid content	%	59 - 61	SR EN ISO 3251
Acid value	mg KOH/g solid resin unit	Max. 6	SR EN ISO 2114
Gardner color, 50% in xylene	-	Max. 4	SE EN ISO 4630
Flow time Φ 4mm DIN cup(20 \pm 0.5°C, 50% in xylene)	seconds	230 - 290	SR EN ISO 2431 PSL-001
Brookfield viscosity, 23°C	mPa	4500 - 6500	SR EN ISO 2555

Additional Information

Density at 20°C	g/cm ³	0.99 – 1.01	SR EN ISO 2811-1
Flash point (closed cup)	°C	28	SR EN ISO 3679

APPLICATIONS

Azalchid E35 - 60X is recommended for air-drying and stoving primers and enamels. Coatings show improved hardness, superior adhesion and excellent resistance to alkali and tropical climate. Air-drying primers and enamels show quick drying time and fast recoatability. High hardness finishes with good color retention can be achieved using amino resins in stoving paints. Aromatic solvents with high boiling point can be used in formulations.

SOLUBILITY

Azalchid E35 - 60X has an extended solubility in solvents based on aromatic hydrocarbons, ether-glycols, esters and ketones and limited solubility in ethanol, butanol or white spirit. It has limited solubility in ethanol, butanol or white spirit.

This information is provided in good faith in order to obtain the best results with AZALCHID, the registered trademark of AZUR S.A. We advise you to verify in advance the information provided in writing or verbally on the technical data sheets or the safety data sheets. The products, processing, or developed applications are your responsibility and we recommend to test our products in advance, or ask for the support of our technicians. Our products are manufactured in accordance with the Integrated Quality Management System ISO 9001: 2015 ISO, 14001:2015 si ISO 45001:2018.

COMPATIBILITY

Azalchid E35 - 60X can be used in combination with melamine and benzoguanamine resins for stoving finishes. It is recommended to check the compatibility level with amino resins in advance. A ratio of 15-20% of melamine resin at temperatures of 140-160°C for a stoving cycle time of 30 minutes gives high hardness finishes.

DRIERS

In air-drying systems recommended siccative levels are 0.02-0.05% cobalt and 0.1-0.3% calcium based on 100% solid resin. Zirconium driers may be co-employed by checking in advance hardness development.

STORAGE

At temperature below 30 °C the product is stable at least 12 months without modification of viscosity or film properties.

SAFETY AND ECOLOGY

Flammable product. Please refer to safety data sheet (MSDS) and consult all information for handling labeling, transport, storage, disposal or ecology procedures.

No. 459 /Ed. 1, Rev. 0



AZUR SA

1-3 Constructorilor Street;
300571, Timisoara

www.azur.ro

This document contains information based on data that is believed to be correct. However, the product may not be applicable to all uses and operating environments. No warranty or guarantee is expressed or implied.

This information is provided in good faith in order to obtain the best results with AZALCHID, the registered trademark of AZUR S.A. We advise you to verify in advance the information provided in writing or verbally on the technical data sheets or the safety data sheets. The products, processing, or developed applications are your responsibility and we recommend to test our products in advance, or ask for the support of our technicians. Our products are manufactured in accordance with the Integrated Quality Management System ISO 9001: 2015 ISO, 14001:2015 si ISO 45001:2018.