

AZALCHID SU59 - 55D40

TYPE

Oxidative drying urethane-alkyd resin, modified with aromatic isocyanate, based on vegetable oil.

DELIVERY FORM

55% solution in D40

FEATURES

Fast drying.
 High film hardness development.
 Air drying or forced stoving primers and enamels.
 Very good gloss and color retention.
 Wood finishes and flooring

SPECIFICATION

Technical characteristics

Property	Unit	Value	Method
Appearance	-	Clear viscous liquid	visual
Solid content	%	54 - 56	SR EN ISO 3251
Acid Value	mg KOH/g solid resin unit	Max. 4	SR EN ISO 2114
Gardner color, 50% in D40	-	Max. 7	SE EN ISO 4630
Brookfield viscosity, 23°C	mPa * sec	1500 - 3500	SR EN ISO 2555
Additional information			
Density at 20°C	g/cm ³	0.91 – 0.93	SR EN ISO 2811-1
Flash point (closed cup)	°C	40	SR EN ISO 3679

Applications

The coatings based on Azalchid SU59-55D40 are fast drying, with high abrasion resistance, improved chemicals and water resistance. The resin is recommended for wood finishes and flooring.

Solubility

It is soluble in aliphatic and aromatic hydrocarbons, esters and ketones. Limited soluble in glycol esters and higher alcohols.

Compatibility

It may be combined with other alkyd resins (medium-oil and long-oil) to improve drying and gloss of decorative coatings.

Driers

The recommended ratio of driers as metals (calculated to 100% resin):

0.10-0.15% Co

0.55-0.65% Zr

0.20-0.30% Ca.

Storage

Store in well-sealed packaging, in sheltered, dry and well-ventilated storage, protected from direct sunlight, at temperatures no higher than 30°C. Storage shelf life – 6 months from date of production.

Safety and ecology

Flammable product. Please refer to safety data sheet (SDS) and consult all information for handling labeling, transport, storage, disposal or ecology procedures.

No.439 / Ed. 1, Rev. 0



AZUR SA

1-3 Constructorilor Street;
300571, Timisoara

www.azur.ro

This document contains information based on data that is believed to be correct. However, the product may not be applicable to all uses and operating environments. No warranty or guarantee is expressed or implied.

This information is provided in good faith in order to obtain the best results with AZALCHID, the registered trademark of AZUR S.A. We advise you to verify in advance the information provided in writing or verbally on the technical data sheets or the safety data sheets. The products, processing, or developed applications are your responsibility and we recommend to test our products in advance, or ask for the support of our technicians. Our products are manufactured in accordance with the Integrated Quality Management System ISO 9001: 2015, ISO14001:2015 și ISO 45001:2018.